




DESCRIPTION	Standard	Requirement	Units	Results
Dry-Tex System				
Ecofit System				
PRODUCT DESCRIPTION				
Surface treatment	-	-	-	Triple-Action Protecsol®
Surface complex	-	-	-	D-Max™ /D-Max + TM
Foam	-	-	-	Double density CXP-HD™
Thickness	EN 428	-	mm	9
Weight	EN 430	-	kg/m ²	5,4
Length	EN 426	-	lm	22 Max
Width	EN 426	-	lm	1.5
SPORT PROPERTIES				
Shock absorption	EN 14808	≥25	%	P2
Vertical deformation	EN 14809	≤3.5	mm	≤3
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
CLASSIFICATION				
Fire	EN 13501-1	-	-	Cfl-s1
Special treatment	-	-	-	Sanosol®
CE MARKING				
	EN 14 904 :2006	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to roaling load