




Technical parameter	Standard	Unit	Result
Construction			heterogeneous
Total thickness	mm	EN 428	1.4
Wear layer thickness	mm	EN 429	0.5
Length of rolls	lm	EN 426	20
Width	m	EN 426	2
Total weight	kg/m <sup>2</sup>	EN 430	1.8
Residual indentation	max. mm	EN 433	0.1
Dimensional stability	max. %	EN 434	±0.2
Curling	max. mm	MSZ EN 434	8
Fire resistance	class	EN 13501-1	B <sub>fl</sub> -s1
	class	DIN 4102/ ÖNORM	B1
Abrasion group	group	MSZ EN 660-1	T
Abrasion resistance	max. m	MSZ EN 423	<250
Light fastness	grade	EN 20105 B02	> 6
Chemical resistance		EN 423	no change
Slip resistance	class	EN 13893	DS
Castor chair resistance		EN 425	no change
Flexibility (diameter 20/40mm)	visual evaluation	MSZ EN 435	no change
Surface treatment			CLP
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
<b>CE MARKING</b>	<b>EN 14041</b>		✓