





# GraboSafe Silver Knight

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	2.0
Wear layer thickness	EN ISO 24340	mm	0.7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2.6
<b>CLASSIFICATION</b>			
European classification	EN 685	class	34/43
Residual indentation	EN ISO 24343	max. mm	0.1
Dimensional stability	EN ISO 23999	max.%	0.2
Light fastness	EN 20105 B02	grade	6
<b>PERFORMANCE</b>			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Bfl-s1
	ASTM E 648 / 662		class1/pass
Slip resistance	DIN 51130		R10
	EN 13893	class	DS
	ASTM D2047-99		dry: 0,96 / wet: 0,89
	RRL Pendulum Test		>36 (wet test)
Abrasion resistance	ASTM D3884-01	g/100 000 c.	-1,04
Chemical resistance	EN ISO 26987		✓
	ASTM F925-02		✓
Castor chair resistance	EN ISO 4918		✓
Surface treatment			TECH Surface
Anti-bacterial and fungicid treatment			Silver Knight
Enviromental attributes		 	Phthalate-, solvent and heavy metal free product
Seaming method			heat or cold weld
<b>Warranty</b>		<b>year</b>	<b>10</b>
<b>CE MARKING</b>	<b>EN 14041</b>		✓