

POLYFLOR CAMARO LOC PU

- Camaro Loc PU - collection of versatile interlocking vinyl floor products
- Wood and stone effect floorcovering designs

SPECIFICATION



4.0mm



0.3mm



15 @ 145.6 x 907.6mm = 1.98m²
 9 @ 177.4 x 1212.4mm = 1.94m²
 11 @ 298.0 x 602.8mm = 1.98m²



7025g/m²



GENERAL PERFORMANCE

EN 649
 EN ISO 10582



REACTION TO FIRE

EN 13501-1 Class Bfl-S1



ABRASION RESISTANCE

EN 649 Group T
 EN ISO 10582 Type 1



SLIP RESISTANCE

EN 13893 Class DS (dry condition)*
 DIN 51130 R10
 AS/NZS 4586 R10

For safety flooring with sustainable wet slip resistance, refer to Expona Control PUR or the Polysafe ranges



ELECTRICAL BEHAVIOUR (body voltage)

EN1815 This product does not accumulate static charges above 2kV and is classified as 'antistatic'. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.



INDENTATION - RESIDUAL

EN 433 <0.05mm
 EN ISO 24343-1 ≤ 0.05mm



DIMENSIONAL STABILITY

EN 434 <0.1%
 EN ISO 23999 ≤ 0.1% max.



CASTOR CHAIR (continuous use)

EN 425 / ISO 4918 Suitable



THERMAL CONDUCTIVITY

Suitable for underfloor heating heating Max 27°C



LIGHT FASTNESS

ISO 105-B02 (Method 3) ≥6



RESPONSIBLE SOURCING

BES 6001 Very good
 SA 8000 Approved factory



VOC EMISSIONS

Indoor Air Comfort GOLD - Eurofins certified product
 AgBB - Very low emissions



ENVIRONMENTALLY PREFERABLE FLOORING

Polyflor Camaro Loc PU achieves a BRE Global Environmental Generic A+ Rating. Camaro Loc PU is 100% recyclable and contains average 40% recycled material. Recyclable via the Recofloor scheme. Visit www.polyflor.com/environment



APPLICATIONS

Polyflor Camaro Loc PU is suitable for most residential interiors and moderate commercial areas. For further information and advice on specific applications, consult polyflor.com or call Polyflor Customer Technical Service on +44 (0)161 767 1912, or email tech@polyflor.com.



For information regarding handling and installation, adhesives, maintenance, applications and chemical resistance, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.

* For clarification regarding slip resistance, consult Polyflor.

VARIATION IN COLOUR AND DESIGN IS A FEATURE OF THESE PRODUCTS INTENDED TO ENHANCE THE NATURAL APPEARANCE OF THE FLOOR.



CAMARO LOC


FLOORING COLLECTION



PERFORMANCE AND PROPERTIES



Refer to BRE Global ratings on www.thegreenguide.org.uk



POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK
 UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551
 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912
 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM
 WEBSITE: WWW.POLYFLOR.COM

James Halstead
 FLOORING



March 2015

POLYFLOR
 COVERING THE WORLD